



TECHNICAL DATA SHEET – RLP® 2378+

Revised: 3/2018

DESCRIPTION

RLP 2378+ is a highly elastomeric, two-component, 100% solids polysulfide based coating for a variety of surface applications. It provides an impermeable yet flexible membrane with excellent resistance to chemical attack and environmental degradation.

TYPICAL APPLICATION

PRIMER	PolySpec 100EX @ 5–7 mils (concrete) or American Safety MS-11CZ LT Primer @ 4–6 mils (steel)
BASECOAT	RLP 2378+ @ 16-20 mils
TOPCOAT	RLP 2378+ @ 16-20 mils
OPTION	Fabric Reinforcement: Geotextile Fabric

PERFORMANCE DATA

TENSILE STRENGTH (ASTM C - 412)	300 psi
ELONGATION (ASTM D - 638)	250%
HARDNESS, SHORE A (ASTM D - 2240)	42-47
OPERATING TEMPERATURE, MAXIMUM	150°F
DRY:	Dependent on chemical exposure
WET:	
VOC	0.00 lb/gal; 0.00 gm/L
VOLUME SOLIDS	100%

BENEFITS

- Impermeable yet flexible membrane
- 100% solids, zero VOC formulation
- Resistant to broad range of fuels and chemicals
- Maintains elasticity at very low temperatures
- Resistant to UV degradation
- Excellent crack-bridging capabilities
- Can be applied directly over elastomeric expansion joint sealants

RECOMMENDED USES

- Primary & secondary containment for water, oil, fuels or other chemical solutions
 - Floating roof tank decks
 - Earthen dike containment membrane*
 - Contaminated or deteriorated concrete*
 - Unsound coated surfaces
- *when applied over geotextile fabric*

GENERIC DESCRIPTION: Epoxy-Modified Polysulfide

STANDARD COLORS: Gray, Black

PACKAGING: 4.5-Gallon Unit

MIX RATIO: 1R: 2H

COVERAGE: 80 ft² / gallon @ 20 mils

RLP® 2378+

CONCRETE, STEEL & EARTHEN DIKE LINING, REINFORCED ELASTOMERIC POLYSULFIDE

STORAGE & INSTALLATION

STORAGE ENVIRONMENT	Dry area, 65–80°F
APPLICATION TEMPERATURE, AMBIENT	50–95°F
APPLICATION TEMPERATURE, SUBSTRATE	Minimum 5°F above dew point
SHELF LIFE	12 months
POT LIFE, @ 77°F	30 minutes
FOOT TRAFFIC, @ 77°F	16 hours
FULL SERVICE, @ 77°F	24 hours / Continuous Immersion: 7 days

SURFACE TEMPERATURE

	65°F	75°F	90°F
RECOAT (MIN)	32 hours	16 hours	6 hours
RECOAT (MAX)	4 days	72 hours	48 hours

CONSIDERATIONS & LIMITATIONS

1. This product is not designed for vehicular traffic.
2. Confirm product performance in specific chemical environment prior to use.
3. Prepare substrate according to "Surface Preparation" portion of this document.
4. Always use protective clothing, gloves and goggles during use. Avoid eye and skin contact. Do not ingest or inhale. Refer to Safety Data Sheet for detailed safety precautions.
5. Do not direct high-pressure spray toward any part of the body. Ensure that all related equipment has proper pressure ratings and that pressure is relieved before servicing equipment.
6. For industrial/commercial use. Installation by trained personnel only.

SURFACE PREPARATION

Refer to PolySpec Surface Preparation Guidelines for more details.

CONCRETE: Apply only to clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants.

STEEL: For immersion service, "White Metal" abrasive blast with an anchor profile of 2–4 mils in accordance with Steel Structures Painting Council Specification SP-5-63 or NACE No. 1 is required. For splash and spillage exposure, "Near White" SP-10-63 or NACE No. 2 is required.

EARTHEN DIKE: (Incorporates a fabric liner.) Grade the dike/basin to promote flow of rainwater or spilled products away from the tank to a sump or collection area. The Thiokol RLP 2378+ fabric liner system may be applied over any type of soil condition as long as the surface profile is smooth and stable. If there is the possibility of puncture from the underside, such as angular rock, install a minimum of 2" of compacted sand to smooth the area. A trench (minimum 1' wide x 1' deep) should be excavated at the top of the dike wall to secure the liner at the completion of the project. See "Fabric Liner" below.

FABRIC LINER

NOTE: Install section of fabric only of a size where the first coat of RLP 2378+ can be applied the same day.

1. Sandblast any concrete or steel to which liner will be adhered.
2. Install non-woven polypropylene fabric (5 oz/yd2 minimum) in precut lengths perpendicular to the slope of the dike. Starting at the high point of the application site, lay out the fabric, overlapping the seams a minimum of 4".
3. Fold back top of overlapped seam and apply 3/8" to 1/2" diameter bead of THIOKOL 2235M Sealant 1" to 2" from edge of bottom sheet of fabric. Fold the top flap onto the base and roll with a metal roller, removing all wrinkles. Any sealant that is squeezed out of the seam should be smoothed.
4. Liner penetrations and connections should use precut skirts of flashing of the fabric liner adhered with 2235M to expedite the installation of the field of fabric liner.

INSTALLATION STEPS

NOTE: For installations over unsound surfaces or earthen dike, fabric liner will be used in lieu of primer. Please refer to "Surface Preparation" and "Fabric Liner" instructions outlined at left.

1. Prime surface with PolySpec Primer. See data sheet for application details.
2. Independently premix each component prior to using in order to disperse any possible settling that may occur during transportation and storage.
3. Prepare and apply RLP 2378+ according to one of the methods outlined below:

A. Plural Component Airless Spray Equipment

(recommended) Plural component airless spray equipment must be capable of heating both RLP 2378+ components to 90–140°F (to improve atomization properties). A static mixer with a minimum of 12 elements should be installed in two locations: 1) where material exits manifold, and 2) before final 6' whip hose going to spray gun. Mix Ratio: 1:2. Tip Size: 0.025–0.029" with a 10" or 12" pattern.

B. Batch Mixing for Roller, Squeegee, Brush, Airless Sprayer

Pour Component A Resin into Component B Hardener pail. Mix well using a mechanical jiffy-type mixer operated at low speed until a consistent color is attained. Scrape container sides to ensure proper blend.

OPTION: If thinning is required, dilute material with 8–10 ounces of xylene per gallon of mixed material. A Graco King pump, minimum of 45:1, can be used. A minimum 3/8" ID fluid line should be used with the shortest possible operating length. A short whip may be used to improve the mobility of the spray gun. Application by roller, squeegee and brush are also suitable methods.

NOTE: Work very quickly due to the product's short pot life (approximately 30 minutes at 77°F). For airless spray applications, the operator must be aware of this issue to prevent material from setting up in pump and lines.

4. After the first coat has become slightly tack free, apply an additional coat of resin/hardener mixture according to Step 3. Be sure first coat is clean and dry before application of second coat.

NOTE: If it has rained or the second coating has not been recoated within 72 hours, the surface must be solvent-wiped to remove dust and dirt. If surfaces are to be recoated after 7 days, the first coat must be scrubbed with a nonmetallic scouring pad or water-blast to remove surface contamination. After the surface is dry, the topcoat may be applied.

5. For earthen dike systems, it is necessary to secure the liner at the top of the berm wall after the RLP 2378+ system has cured. This is accomplished by backfilling the trench with soil, rounded gravel or using a "deadman" post.
6. Always wear gloves when using this product.

1R:2H / DOC RLP2378+-TDS

© Copyright 2018 ITW Polymers Sealants North America, Inc. All rights reserved. Published technical data and instructions are subject to change without notice. Please visit the online catalog at www.polyspec.com for the most current technical data and instructions. Or, you may contact your ITW Polymers Sealants North America, Inc. representative for current technical data and instructions.

ITW Polymers Sealants North America, Inc. warrants its products to be free from defects in material and workmanship. ITW Polymers Sealants North America, Inc.'s sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW Polymers Sealants North America, Inc.'s option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW Polymers Sealants North America, Inc. in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW Polymers Sealants North America, Inc. of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ITW Polymers Sealants North America, Inc. makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Polymers Sealants North America, Inc. be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ITW Polymers Sealants North America, Inc. whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW Polymers Sealants North America, Inc. can not guarantee that color will conform to sample, if provided.